## **PRODUCT INFORMATION**

Purgex<sup>™</sup> 742 Commercial Purging Compound is engineered specifically for polypropylene copolymer applications. Like its predecessors, Purgex<sup>™</sup> 742 has non-toxic, non-abrasive active ingredients with a polyethylene carrier. This product provides dual-cleaning action with a mechanical component and a unique active ingredient. Purgex<sup>™</sup> 742 is a ready-to-use blend which effectively removes contamination from the screw, barrel and hot runner system. Purgex<sup>™</sup> 742 is designed to reduce the standard amount of purging compound used, to significantly reduce purge time, and to minimize scrap. All active ingredients in Purgex<sup>™</sup> 742 are Generally Recognized As Safe (GRAS) by the US FDA.

## **Physical Description:**

- Blend, polyethylene, and an active component
- Non-toxic, non-abrasive, and safe
- Ready to use and easy to remove

Process:	Ø	Injection Molding		Injection Blow Molding		Extrusion-Blow Molding		Extrusion- Profile
	Ø	Extrusion- Compounding	Ŋ	Extrusion- Sheet		Blown Film		
Works Best on These Resins:	Ø	PP Copolymer						
Also Useful for:	Ø	PP Homopolymer	Ø	PE	N	LDPE		
Amount Needed:	1 barrel capacity, depending upon condition of machine/tool and coolant/additive loading.							
Temperature Range:	375°F to 475°F (191°C to 246°C)							
Recommended for:	Ø	Hot Runners	M	Mixing Nozzles	M	Check Valves		Accumulators
	M	Cold Runners		Extrusion Dies	M	Melt Pumps		

## Features & Benefits:

- High efficiency purging compound specifically designed for polypropylene copolymer applications for injection molding of interior trim parts.
- ✓ Reduced amount is required for efficient purging and low scrap.
- Effectively cleans the barrel, screw, check ring, as well as hot runner systems and is safely processed through tools with valve gates.
- $\checkmark$  Is easily removed from the system with the next production resin.
- ✓ With regular use, Purgex<sup>™</sup> forms a temporary barrier which protects steel surfaces, extending the cleaning process.

Copyright 2013 Neutrex, Inc. All rights reserved - Revision 0: 2/28/13