

**CP PBT CB530G**

PBT Alloy, Glass fiber 30% reinforced

Properties	Test Method	Unit	Value
<b>Physical Properties</b>			
Resin Identification	ISO 1043		PBT Alloy-GF30
Density	ISO 1183	g/cm <sup>3</sup>	1.56
ASH	ISO 1172	%	30
Mold Shrinkage	ISO 294	%	
Water Absorption (23 °C , 50 % RH)	ISO 62	%	0.03 - 0.07
<b>Mechanical Properties</b>			
Tensile Strength	ISO 527	Mpa	160
Elongation at Break	ISO 527	%	3.0
Flexural Strength	ISO 178	MPa	245
Flexural Modulus	ISO 178	MPa	10000
Charpy Impact Strength (Un-Notched)	ISO 179	KJ/m <sup>2</sup>	
Charpy Impact Strength (Notched)	ISO 179	KJ/m <sup>2</sup>	9.0
Rockwell Hardness (R-scale)	ISO 2039		119
<b>Thermal Properties</b>			
Melting Point (20 °C/min)	ISO 11357	°C	220/250
Heat Deflection Temperature (1.8 MPa)	ISO 75	°C	205
Flammability (t = 0.8mm)	UL94	Class	HB
<b>Electrical Properties</b>			
Dielectric Constant	ISO 60250	kV/mm	
Dissipation Factor	ISO 60250	4.E+04	
Volume resistivity	IEC 60093	Ω · cm	10 <sup>16</sup>
<b>Injection Molding Condition</b>			
Mold Temperature		°C	70 - 90
Injection Molding Temperature		°C	240 - 270
Pre-drying Temperature		°C	120 - 130
Pre-drying Time			3 - 5

The above material properties are measured based on our knowledge and relevant test methods and conditions. The data provided should not be used to establish specification limits nor used along as the basis of design. We recommend that the customer must make their own determination as to its suitability to their purpose prior to use.